



PLASTICIZERS

Sales Specifications
Rev. 5 (7/1/01)

JAYFLEX™ L911P Plasticizer Di-L-(nonyl, undecyl) Phthalate

Product Description



Excellent linear plasticizer for superior performance with good processibility

- Low volatility/fogging characteristics
- Good low temperature flexibility
- Excellent oven-aged retained elongation properties

Applications

- Wire and cable insulation for automotive and communications
- Low temperature, high performance film and sheeting
- Low fogging automotive interiors

Theoretical Mol. Wt. : 446



Properties	Test Methods	Sales Specifications
Acidity, as phthalic acid, wt%	BRCP 4625	0.015 max
Appearance	BRCP 4065	Clear and Free
Color, Platinum Cobalt	BRCP 4273	50 max
Ester Content, wt%	BRCP 4630	99.6 min
Odor	BRCP 4550	Characteristic
Specific Gravity, 20/20°C	BRCP 4843	0.958 - 0.964
Water Content, wt%	BRCP 5053	0.1 max

CAS Registry number 68515-43-5

Jayflex is a trademark of Exxon Mobil Corporation. Imperial Oil is a licensee.

For more information, to request samples and/or to place orders, call: 1 (800) 663-4109

The user may forward, distribute, and/or photocopy this copyrighted document only if it is unaltered and complete. You may not copy this document to a Web site. This information relates only to the material designated and may not be valid for such material used in combination with any other materials or in any process. Typical values are representative of production, may vary over time and may not match the date of publication. All information, to the best of our knowledge and belief, is accurate and reliable as of the date compiled. Moreover, no warranty or guarantee is made as to its accuracy, reliability or completeness nor do we offer any warranty against patent infringement. It is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Sampling and testing procedures in effect at the time of production will be used for certification testing. Results may be based on tank certification, manufacturing data, periodic testing, compliance testing, shipment, end of run, rundown tank or most recent restock analysis. We reserve the right to use other test methods in certifying this material.